




SOFT ALPET

ANTI-MOISTURE SHEET SF-7006

PRODUCT INFORMATION


Attached woven with the VMPET to **maximize the insulating effect of the film (non-metallic)** and to **maximize water of moisture** barrier properties and increase the tension strength.



click to
MSDS

SOFT ALPET

ANTI-MOISTURE SHEET SF-7006



PHYSICAL CHARACTERISTICS

Description	Parameter	Test Method
Vapour barrier	High	ASTM E96
Tensile strength Machine Direction	601N/5cm	ASTM D4595
Tensile strength Lateral Direction	480N/5cm	
Edge tear resistance Machine Direction	118N	TAPPI T470
Edge tear resistance Lateral Direction	112.3N	
Anti Moisture	0.4/m3/24h	JIS Z 0208
Width : 1000mm / 1250mm / 1500mm		
100±5GSM		

SOFTBAG KOREA CO.,LTD.

6FL, Shingang Bldg,
67, Seongsui-ro,
Seongdong-gu,
Seoul, KOREA

Tel. 82-2-462-1401

Fax. 82-2-462-1402

Email: kenny@softbagkorea.com

click to
Contact us